

## Starfish Diamond

To encase:

Do not touch stone with your hands. If you have, clean stone with 90% alcohol and dry.

Drop cold clean stone into cold encasement tube.

Place tube with stone in it into 1100 F kiln.

Preheat for 6 minutes.

Start encasing slowly with a proper flame.

Make sure the stone is positioned so the culet is forward , and the table is facing back at a 45 degree angle.